



## ATLAS-SVM SUPER VINYL MATT

### DESCRIPTION

Atlas-SVM is a water-thinnable emulsion especially formulated to give a high finish for all normal interior and exterior wall and ceiling surfaces. It is tough, hard wearing scrub resistant offering excellent washability.

### PROPERTIES

**TYPE:** Water-thinnable based on a copolymer emulsion.  
**DRYING TIME:** 1 to 2 hours under normal conditions i.e. 20°C. Re-coatable after 2 to 3 hours  
**COVERING RATE:** 65 to 75 square meters per US Gallon depending on the porosity of the surface.  
**LEAD CONTENT:** Not applicable.  
**FLASH POINT:** Not applicable.  
**APPLICATION METHODS:** Brush, roller or conventional or airless spray gun.

### SYSTEMS

#### **PREPARATION:**

Prepare the surface as appropriate.  
Surfaces should be clean, dry and free from grease or oil.  
Remove all loose flaking material.  
New surfaces should be primed with Atlas-Primer Sealer mixed with 25% of water; Old surfaces prime with Isoflex-FCW.

#### **FINISHING:**

Apply two or three coats of Atlas-MV by brush, roller or spray gun.

### APPLICATION

#### **BRUSH & ROLLER :**

If thinning is necessary, add up to one part of water to four parts (by volume) of Atlas-SVM and apply two coats.  
To ease application on very porous surfaces, thin the first coat with up to equal parts (by volume) of water and apply a further two coats thinned as required.  
When applying by brush, load the brush fairly generously, apply a full even coat and do not brush out too far.  
When applying by roller, stir the paint to a smooth consistency before pouring into the roller tray.

Apply with a light even pressure to the roller avoiding excessive pressure at the edges, taking care not to over spread.

#### **CONVENTIONAL SPRAY GUN :**

Thin by adding 1 to 2 parts of water to 5 parts (by volume) of paint.

#### **AIRLESS SPRAY GUN :**

Application details vary but a typical recommendation is:  
**Thinning** - thin by adding 1 to 2 parts of water to 4 parts (by volume) of paint.  
**Min. working pressure on paint:** 2000 lb/sq.in.  
**Spray tip aperture size :** 17 thou  
**Spray tip angle :** 80°

#### **CLEANING OF TOOLS**

Use cold water when wet, and turpentine, or white spirit when dry.  
During work, place tools in water when not in use.

#### **PACKING**

Atlas-SVM is offered in the market in One and Five US Gallons.

#### **TECHNICAL SERVICE**

The Technical Department is available to assist you in the correct use of our products and its resources are at your disposal entirely without obligation.

Contact:

**Société Raymond Barakeh SAL**  
**P.O.Box 119737 – Beirut – LEBANON**

Phone : 00 961 1 690594 – 3 260989

Fax: 00 961 1 690594

[info@barakeh.com](mailto:info@barakeh.com)

[www.barakeh.com](http://www.barakeh.com)

Atlas Paints is a registered trademark of Société Raymond Barakeh SAL

Visit our website at [www.barakeh.com](http://www.barakeh.com)

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate and is offered for the user's consideration investigation and verification, but we do not warrant the results to be obtained. Please read all statements, recommendations, or suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation or suggestion is intended for any use which would infringe any patent or copyright.  
Société Raymond Barakeh SAL P.O.Box 119737 – Beirut – LEBANON

