

PRODUCT DATA SHEET

PRODUCT NAME

Raymix – BWP (Rubberized Bitumen)

MANUFACTURER

Société Raymond Barakeh SAL.
Bauchrieh, Industrial City, Sector 7, 40 – Street 86
Ph. 00961 1 690594 www.barakeh.com Beirut – Lebanon.

DESCRIPTION

Raymix – BWP is a black colour, cold applied rubberised bituminous solution designed as a protective coating with excellent adhesion to concrete, masonry and asphalt.
Conforms with B.S. Code

PHYSICAL AND CHEMICAL CHARACTERISTICS

Styrene Butadiene Rubberized Bitumen.	
Rubber Content	Approx. 35%
Aspect	Viscous solution.
Colour	Black.
Specific Weight	0.90 Kg/Litre.
Solvent	Thinner
Elongation	Min. 2000%
Covering Capacity	Approx. 1.5 m ² /litre/Coat

The information and data given is to the best of our knowledge reliable, but is given without obligation.

METHOD OF APPLICATION

By brush, roll or spray.

FUNCTION

Raymix-BWP may be applied successfully to a wide range of surfaces:

- Concrete.
- Masonry.
- Asphalts.
- Slate.
- Lightweight concrete screeds.

CONTAINER SIZES

FIVE US Gallons.

STORAGE LIFE

12 months in undamaged, tightly sealed containers.

PROPERTIES

Raymix-BWP has excellent properties as a protective coating, including low permeability to moisture and weathering resistance.

COVERAGE

The application of **Raymix-BWP** varies according to the porosity of the surface.

- As a general rule apply a litre in an area of approximately 1.5 m².

APPLICATION INSTRUCTIONS

- Surface to be coated with **Raymix-BWP** should be clean, dry and exempt from all oil, grease, dirt, dust and loose debris.
- Surfaces should be dry.
- First coat of **Raymix-BWP** should be diluted with an equal volume of Thinner and allowed to dry applying second coat.

- The second coat should be applied evenly across the surface in one generous coating.
- **Raymix-BWP** resists to rainfall within 20-30 minutes of its application.

NOTE

In order to comply with BS Code of Practice 144: Part 3: Clause 4.6.1., it is essential that after priming concrete or screed surfaces the coating is completely free of all solvent and therefore a safe drying margin of 2 hours should be allowed.

CLEANING TOOLS

Tools may be cleaned with thinner. Spillages should be wiped off surfaces before the compound has set.

TECHNICAL SERVICE

The Technical Department is available to assist you in the correct use of our products and its resources are at your disposal entirely without obligation.

HEALTH & SAFETY

For further information see the Raymix-BWP Material Safety Data Sheet, or consult Société Raymond Barakeh SAL.

STORAGE

Raymix-BWP requires should preferably be stored protected from frost. If the product does become frozen it should be carefully mixed after thawing out to restore it to its normal state facilities.

TECHNICAL SERVICE

The Technical Department is available to assist you in the correct use of our products and its resources are at your disposal entirely without obligation.

Contact:

Société Raymond Barakeh SAL
P.O.Box 119737 – Beirut – LEBANON

Phone : 00 961 1 690594 – 3 260989

Fax: 00 961 1 690594

E.Mail : info@barakeh.com

[Http://www.barakeh.com](http://www.barakeh.com)

PRODUCT WARNING

Société Raymond Barakeh SAL has no control over the use or storage of this product and therefore does not accept any liability in this regard. Any verbal advice given should not be regarded as authoritative information. This information is subject to change without notice, therefore all applicators should ensure they have current information. This product is intended for the use only of skilled tradesmen and where applicable, statutory licensed tradesmen experienced and trained in the use of this product. This product is warranted to be of uniform quality within the manufacturer's tolerance. This manufacturer has no control over the use or misuse of this product, therefore no warranty rests or implied, is or can be made either as to the effects of such use. The manufacturer's obligations shall be limited to replacing product proving to be defective.